



Specifications

C2S Art Paper /Gloss(Nevia)

Mar. 2024

Item	Unit	Test Method Reference	80 g/m ²	90 g/m ²	100 g/m ²	105 g/m ²	115 g/m ²	120 g/m ²	128 g/m ²	130 g/m ²
Basis Weight	g/m ²	ISO 536	80±3	90±3	100±4	105±4	115±4	120±4	128±4	130±4
Thickness	μm	T 411	65±4	73±4	81±4	86±4	94±4	98±4	105±4	107±4
Brightness	%	ISO 2470-1	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2
Opacity	%	ISO 2471	≥89	≥91	≥93	≥93	≥95	≥95	≥96	≥96
Roughness	μm	ISO 8791-4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4
Gloss	%	T 480	70±5	70±5	70±5	70±5	70±5	70±5	70±5	70±5

GOLD EAST PAPER (JIANGSU) CO.,LTD.

Q.A.D.





Specifications

C2S Art Paper / Matt(Nevia)

Mar. 2024

Item	Unit	Test Method Reference	80 g/m ²	90 g/m ²	100 g/m ²	105 g/m ²	115 g/m ²	120 g/m ²	128 g/m ²	130 g/m ²
Basis Weight	g/m ²	ISO 536	80±3	90±3	100±4	105±4	115±4	120±4	128±4	130±4
Thickness	μm	T 411	72±4	78±4	91±4	95±4	106±4	111±4	118±4	120±4
Brightness	%	ISO 2470-1	90±2	90±2	90±2	90±2	90±2	90±2	90±2	90±2
Opacity	%	ISO 2471	≥88	≥89	≥93	≥93	≥94	≥95	≥95	≥95
Roughness	μm	ISO 8791-4	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0	≤3.0
Gloss	%	T 480	35±5	35±5	35±5	30±5	30±5	30±5	30±5	30±5

GOLD EAST PAPER (JIANGSU) CO.,LTD.

Q.A.D.

